

Pola L

SCHEMA TECNICA

Composizione

100% Poliestere FR - Trevira CS

Peso

gr./mtl. 420 ± 5%

Altezza

cm. 140 ± 2%

Lunghezza Pezze

mt. 65 ± 5%

Abrasion

Test Martindale
UNI EN ISO 12947:2000
25.000 cicli ± 5.000

Solidità Luce

(Xenotest) UNI EN ISO 105 B02
5 ± 1

Pulizia

Non spazzolare e usare con regolarità
l'aspirapolvere

Lavaggio



Omologazioni

Le proprietà ignifughe sono
intrinseche nella fibra e non
da trattamenti aggiuntivi.

I Classe 1


F M1

D B1 DIN 4102

GB BS 5852 Crib 5 in combination
with CMHR 35 foam

EN 1021 Part. 1-2

Azimut serie Pola L

 IMO 688 (17) - IMO 563 (14)
IMO 653 (16)

TECHNICAL DATA

Composition

100% Polyester FR - Trevira CS

Weight

gr./lm. 420 ± 5%

Width

cm. 140 ± 2%

Piece Length

lm. 65 ± 5%

Abrasion Test

Martindale
UNI EN ISO 12947:2000
25.000 turns ± 5.000

Lightfastness

(Xenotest) UNI EN ISO 105 B02
5 ± 1

Cleaning

Do not brush and use the
vacuum-cleaner regularly

Washing



Approvals

The flame-retardant properties
are inherent to the fibre and are
not provided by additional
treatments.

I Class 1

F M1

D B1 DIN 4102

GB BS 5852 Crib 5 in combination
with CMHR 35 foam

EN 1021 Part. 1-2

Azimut type Pola L

 IMO 688 (17) - IMO 563 (14)
IMO 653 (16)

